



Arcanol Rolling Bearing Greases

Grease selection for typical applications



FAG Arcanol Greases

	Designation	Characteristic applications	Operating temperature °C		Continuous limit temperature °C	Thickener	Base oil	Consistency NLGI	Base oil viscosity at +40 °C mm ² /s	Temperatures		Low friction, high speed	High load, low speed	Vibrations	Support for seals	Relubrication facility	
			from	to						low	high						
Multipurpose greases	MULTITOP	Ball and roller bearings in rolling mills, construction machinery, automotive engineering, spinning and grinding spindles	-50 ¹⁾	+140	+80	Lithium soap	Partially synthetic oil	2	82	++	+	+	++	+	•	++	
	MULTI2	Ball bearings up to 62 mm outside diameter in small electric motors, agricultural and construction machinery, household appliances	-30	+120	+75	Lithium soap	Mineral oil	2	110	+	•	•	•	•	•	•	++
	MULTI3	Ball bearings from 62 mm outside diameter in large electric motors, agricultural and construction machinery, ventilators	-30	+120	+75	Lithium soap	Mineral oil	3	80	+	•	•	•	+	+	+	+
High loads	LOAD150	Ball, roller, and needle roller bearings, linear guidance systems in machine tools	-20	+140	+95	Lithium complex soap	Mineral oil	2	160	•	+	—	++	+	+	+	+
	LOAD220	Ball and roller bearings in rolling mills, rail vehicles, paper machinery	-20	+140	+80	Lithium/calcium soap	Mineral oil	2	245	•	+	—	++	+	+	+	+
	LOAD400	Ball and roller bearings in mining machinery, construction machinery, main bearings for wind turbines	-40	+130	+80	Lithium/calcium soap	Mineral oil	2	400	•	•	—	++	+	+	+	+
	LOAD460	Ball and roller bearings, wind turbines, bearings with pin-type cage	-40 ¹⁾	+130	+80	Lithium/calcium soap	Mineral oil	1	400	+	•	—	++	+	—	—	+
	LOAD1000	Ball and roller bearings in mining machinery, construction machinery, cement plants	-30 ¹⁾	+130	+80	Lithium/calcium soap	Mineral oil	2	1000	•	•	---	++	+	+	+	+
High temperature ranges	TEMP90	Ball and roller bearings in clutches, electric motors, automotive engineering	-40	+160	+90	Poly-carbamide	Partially synthetic oil	3	148	++	+	•	•	•	•	+	+
	TEMP110	Ball and roller bearings in electrical equipment, automotive engineering	-35	+160	+110	Lithium complex soap	Partially synthetic oil	2	130	++	++	+	•	•	•	•	•
	TEMP120	Ball and roller bearings in continuous casting plants, paper machinery	-30	+180	+120	Poly-carbamide	Synthetic oil	2	400	+	++	—	++	•	+	•	•
	TEMP200	Ball and roller bearings in guide rollers in baking machinery, kiln trucks and chemical plants, piston pins in compressors	-30	+260	+200	PTFE	Alkoxy fluoro oil	2	550	+	++	---	+	•	•	•	•
Special greases	SPEED2,6	Ball bearings in machine tools, spindle bearings, rotary table bearings, instrument bearings	-40	+120	+80	Lithium complex soap	Synthetic oil	2 – 3	25	++	•	++	---	—	•	•	
	VIB3	Ball and roller bearings in blade adjusters in wind turbine rotors, packaging machinery, rail vehicles	-30	+150	+90	Lithium complex soap	Mineral oil	3	170	+	+	—	+	++	+	—	
	FOOD2	Ball and roller bearings in applications with food contact (NSF-H1 registration, kosher and halal certification)	-30	+120	+70	Aluminum complex soap	Synthetic oil	2	150	+	—	•	•	•	•	•	++
	CLEAN-M	Ball, roller, and needle roller bearings as well as linear guidance systems in clean room applications	-30	+180	+90	Poly-carbamide	Ether oil	2	103	++	++	•	•	•	•	•	+
	MOTION2	Ball and roller bearings in oscillating operation, slewing rings in wind turbines	-40	+130	+75	Lithium soap	Synthetic oil	2	50	++	•	—	+	++	+	•	

¹⁾ Measurement values according to Schaeffler FE8 low temperature test.

++ extremely suitable | + highly suitable | • suitable | — less suitable | --- not suitable

Typical applications **Typical applications**

MISCIBILITY OF BASE OILS AND THICKENERS

Caution must always be taken when mixing different lubricants. On the one hand, lubricating oils and the base oils and thickeners used in greases may be incompatible (refer to tables 1 and 2). On the other hand, the effect of additives and the performance capability of lubricant mixtures cannot be estimated without the appropriate tests being carried out.

If technical conditions make it impossible to avoid lubricants becoming mixed, the risk that should be expected in terms of reduced performance and lubricant incompatibility can at least be estimated using the tables. In such cases, expert advice from lubricant experts is generally recommended – from the Lubricant Technology department at Schaeffler Technologies AG & Co. KG, for example.

Base oil	Mineral oil	Polyalphaolefin	Esters	Polyglycol	Perfluoropolyether
Mineral oil	+	+	?	-	-
Polyalphaolefin	+	+	?	-	-
Esters	?	?	+	?	-
Polyglycol	-	-	?	+	-
Perfluoropolyether	-	-	-	-	+

▲ Table 1: Base oil miscibility*

Thickener	Lithium soap	Lithium complex	Calcium complex	Lithium/calcium soap	Aluminum complex	Polycarbamide	PTFE
Lithium soap	+	+	?	+	-	?	+
Lithium complex	+	+	+	+	?	?	+
Calcium complex	?	+	+	+	?	+	+
Lithium/calcium soap	+	+	+	+	-	+	n. s.
Aluminum complex	-	?	?	-	+	?	+
Polycarbamide	?	?	+	+	?	+	+
PTFE	+	+	+	n. s.	+	+	+

▲ Table 2: Compatibility of different thickener types*

*Excerpts quoted according to the Society for Tribology (Gesellschaft für Tribologie e.V.), worksheet 9, "Lubricating systems", October 2015

+ Miscibility normally good	- Normally not miscible	? Mixing often causes reduced performance capability; miscibility should be checked	n. s. not specified
-----------------------------	-------------------------	---	---------------------

Schaeffler Technologies AG & Co. KG

Georg-Schaefer-Str. 30

97421 Schweinfurt

Germany

Internet www.schaeffler.de/en/services

E-Mail industrial-services@schaeffler.com